

ISOMAT AK-ELASTIC

High performance, two-component elastic tile adhesive

Description

ISOMAT AK-ELASTIC is a 2-component elastic tile adhesive. It consists of a cement-based powder mortar (component A) and a resin emulsion (component B). It provides high initial and final adhesive strength, exceptional elasticity and moisture resistance. It possesses increased open time for application.

It is classified as type C2 E S2 adhesive according to EN 12004.

Adhesive strength after:

- 28 days: $\geq 3,00 \text{ N/mm}^2$
- heating in $+70^\circ\text{C}$: $\geq 3,00 \text{ N/mm}^2$
- immersion in water: $\geq 1,50 \text{ N/mm}^2$
- 25 freeze-thaw cycles: $\geq 1,70 \text{ N/mm}^2$

Temperature resistance: from -30°C to $+90^\circ\text{C}$

Deformation ability according to EN 12002: $> 5 \text{ mm}$

All measurements were conducted according to EN 12004-2.

Fields of application

ISOMAT AK-ELASTIC is suitable for fixing ceramic or natural stone tiles on walls or floors, on vibrative or dimensionally unstable substrates like gypsum board, chipboard, floors with in-floor heating, terraces, balconies, swimming pools, etc. It is also suitable for fixing large tiles as well as new tiles on old tile layers.

Suitable for indoor or outdoor use.

Combined with the 2-component brushable sealing slurries AQUAMAT-FLEX and AQUAMAT-ELASTIC, it provides a perfect system for sealing and fixing.

Directions for use

1. Substrate

The surface to be overlaid must be clean, free of dust, grease, paint, loose material etc. Dampening of the substrate before application is recommended.

2. Application

The content of the 25 kg bag (component A) is added into the 10 kg of liquid (component B) under continuous stirring, until a homogenous paste is formed. A low revolution mixer is recommended for mixing.

The mixture should be left about 10 min to settle and should be stirred slightly again.

The tile adhesive should be spread and "combed" on the substrate using a notched trowel, in order to be applied uniformly on the whole surface. The tiles should be then fixed by pressing them in the desired position.

The spread mixture should be covered with tiles within 30 min in order to avoid skin formation, i.e. before the adhesive film starts setting.

Technical data

	<u>Component A</u>	<u>Component B</u>
Basis:	cementitious powder	water dispersion of acrylic polymer
Color:	white	white
Mixing proportion:	2,5 parts by weight	1 part by weight

Combined product

Application temperature:	from $+5^\circ\text{C}$ to $+35^\circ\text{C}$
Application thickness:	up to 10 mm
Pot life:	at least 8 h
Open time:	at least 30 min
Minor adjustments open time:	at least 30 min
Pointing on walls:	after 6-12 h
Pointing on floors:	after 24-48 h

Consumption

1,5-4,0 kg/m^2 , depending on the trowel's notch size and the nature of the substrate.

Packaging

Combined 35 kg package (25 kg cement-based powder mortar bag + 10 kg emulsion resin plastic container).

ISOMAT AK-ELASTIC

Storage

Component A:

12 months from production date if stored in original, unopened packaging, in places protected from moisture and frost.

Component B:

12 months from production date if stored in original, unopened packaging, in temperature between +5°C and +35°C. Protect from direct sun exposure and frost.

Remarks

- The A-component of ISOMAT AK-ELASTIC contains cement and reacts as alkaline with moisture, so it is classified as irritant.
- Very porous surfaces such as aerated concrete, gypsum boards, chipboards etc. must be primed first with UNI-PRIMER acrylic primer.
- In case ISOMAT AK-ELASTIC is used for the adhesion of non-absorptive tiles on non-absorptive substrates, the setting time of the adhesive might be prolonged.
- Consult usage risks and safety advice written on the bag.



ISOMAT S.A.

17th km Thessaloniki – Ag. Athanasios
P.O. BOX 1043, 570 03 Ag Athanasios, Greece
08

EN 12004:2007+A1:2012
DoP No.: ISOMAT AK-ELASTIC/1036-01
NB: 2032

Improved highly deformable cementitious adhesive with extended open time, for internal and external tiling.

Reaction to fire	Class E
Release of dangerous substances	See MSDS
Bond strength, as:	
- initial tensile adhesion strength	≥ 1 N/mm ²
Durability, for	
- tensile adhesion strength after heat ageing	≥ 1 N/mm ²
- tensile adhesion strength after water immersion	≥ 1 N/mm ²
- tensile adhesion strength after freeze thaw cycles	≥ 1 N/mm ²

ISOMAT S.A.

BUILDING CHEMICALS, MORTARS & PAINTS
HEADQUARTERS – THESSALONIKI, GREECE
17th km Thessaloniki – Ag. Athanasios Road
P.O. BOX 1043, 570 03 Ag. Athanasios, Greece
T +30 2310 576000

www.isomat.eu e-mail: support@isomat.eu