

Technical Datasheet

ISOMAT PROFESSIONAL ACRYL

100% acrylic paint for exterior use, ideal for professionals

Description

ISOMAT PROFESSIONAL ACRYL is a matt 100% acrylic paint for exterior use, ideal for professionals. Suitable for new or old surfaces requiring frequent repainting, such as in public buildings, hotels, hospitals, schools, etc., as well as surfaces stained with graffiti. Features high opacity and surface coverage while offering great workability and flow. Has high resistance to weather conditions and aging, as well as quick-drying and recoat times. Offers a beautiful matt finish.

The white is certified as cool paint.

Certified according to EN 1504-2 and classified as a coating for surface protection of concrete. CE marked. Certificate No.: 2032-CPR-10.11.

Fields of application

ISOMAT PROFESSIONAL ACRYL is used on new or old exterior surfaces, including concrete, render, brickwork, gypsum board, asbestos cement, wood, etc. Suitable also for surfaces treated with acrylic or cementitious fillers.

Technical data

Colors:	white and selected colors through ISOMAT COLOR SYSTEM
Type:	100% acrylic paint
Volume solids:	40 ± 2%
Dry film thickness: (EN ISO 2808)	30 ± 2 µm
Wet film thickness: (EN ISO 2808):	68 ± 5 µm
Viscosity: (EN ISO 2884- 2)	115 ± 5 KU
Density (WHITE): (EN ISO 2811- 1)	1.44 ± 0.03 kg/l
pH: (EN ISO 4316)	8-9.5

Adhesion: ≥ 2.25 N/mm²
(EN ISO 4624)

Vapor permeability: Sd = 0.06 ± 0.02 m
(EN ISO 7783- 2: V₁ high, < 0.14)

Capillary water absorption: w = 0,07 ± 0,02 kg/m².h^{0.5}
(EN ISO 1062- 3: W₃ low, w < 0.10 kg/m².h^{0.5})

Drying time: ~ 1 h (touch dry)
(EN ISO 9117)

Recoat time: 3-4 h
(EN ISO 9117)

VOC content: 15.8 g/l

Gloss level: < 10 at 85°
(EN ISO 2813)

Whiteness: ≥ 86%
(EN ISO 6504- 3)

Cleaning of tools:

Remove as much paint as possible from application tools before cleaning. Clean tools thoroughly with water and detergent immediately after use.

Directions for use

1. Substrate preparation

The substrate should be dry and free of grease, loose particles, dust, etc.

- Cracks or joints are filled with ISOMASTIC-A acrylic sealant or ISOMAT ACRYL-STUCCO acrylic filler.
- Any imperfections in concrete should be patched with DUROCRET polymer-modified mortar, while imperfections in exposed concrete should be treated with PLANFIX or PLANFIX-FINE polymer-modified fillers.
- Plastered wall may be patched with UNICRET and UNICRET-FAST premixed mortars.

The substrate should be primed with the concentrated, acrylic water-based primer ISOMAT PROFESSIONAL PRIMER, thinned 300-400% with clean water.

Loose or crumbly substrates should be primed with the silicone-acrylic, micronized, water-based primer PRIMER ACRYL, thinned up to 50% with clean water.



ISOMAT PROFESSIONAL ACRYL

2. Application

Before use, ISOMAT PROFESSIONAL ACRYL should be thoroughly stirred. It is applied as is or thinned 5-10% with clean water in two coats, using a roller, brush or airless spray. The second coat is applied after the first one has completely dried. Temperature during application and drying of the paint should be between +10°C and +35°C.

Coverage

ISOMAT PROFESSIONAL ACRYL covers approx. 12 m²/l per coat, when applied on previously prepared surfaces.

Packaging

ISOMAT PROFESSIONAL ACRYL is supplied in 0.75 l, 3 l and 9 l containers.

Shelf life – Storage

24 months from production date if stored in original, unopened packaging, at temperatures between +5°C and +35°C. Protect from direct sunlight and frost.

Volatile Organic Compounds (VOCs)

According to Directive 2004/42/CE (Annex II, table A), the maximum allowed VOC content for the product subcategory c, type WB, is 40 g/l (2010) for the ready-to-use product.

The ready-to-use product ISOMAT PROFESSIONAL ACRYL contains a maximum of 40 g/l VOC.



2032

ISOMAT S.A.

17th km Thessaloniki – Ag. Athanasios
P.O. BOX 1043, 570 03 Ag Athanasios, Greece

16

2032-CPR-10.11

DoP No.: ISOMAT PROFESSIONAL ACRYL

/ 1427-03

EN 1504-2

Surface protection products

Coating

Permeability to CO₂: Sd > 50m

Water vapor permeability: Class I (permeable)

Capillary absorption: $w < 0.1 \text{ kg/m}^2 \cdot \text{h}^{0.5}$

Adhesion: $\geq 1.0 \text{ N/mm}^2$

Dangerous substances comply with 5.3

Reaction to fire: Class F

ISOMAT S.A.

BUILDING CHEMICALS, MORTARS & PAINTS

HEADQUARTERS – THESSALONIKI, GREECE

17th km Thessaloniki – Ag. Athanasios Road

P.O. BOX 1043, 570 03 Ag. Athanasios, Greece

T +30 2310 576000

www.isomat.eu e-mail: support@isomat.eu