

ISOPAST

Bituminous waterproofing emulsion

Description

ISOPAST is a water-based, solvent-free, waterproofing bituminous emulsion consisting of resins and mineral stabilizers.

It shows excellent adhesion to various substrates such as concrete, metal, wood, polyurethane, polystyrene, etc. It is applicable in slightly damp substrates.

After hardening it forms a membrane that is resistant to low concentration acids and bases, and it remains unaffected by subsoils minerals.

ISOPAST meets the requirements of ASTM D-1227, Type III, Class 2.

Fields of application

ISOPAST is used for waterproofing and protection of concrete surfaces, including flat roofs, roofs, floors, external walls, foundations, etc. Moreover, it can be used as primer prior to bonding bituminous waterproofing membranes and for maintenance of existing bituminous layers.

Technical data

Form:	thixotropic paste
Color:	brown-black
Density (EN ISO 2811-1):	1.10-1.20 g/cm ³ (+20°C)
Residue by evaporation:	40% - 60%
Drying time:	≤ 24 h

Cleaning of tools:

Tools must be cleaned thoroughly with water, immediately after use. After hardening, tools should be cleaned with gasoline or diesel.

Directions for use

1. Substrate

Substrate must be clean, dry, free of dust and loose materials.

2. Application

ISOPAST should be thoroughly stirred before application. It is applied by roller, brush or, airless spray.

For waterproofing and protection:

ISOPAST is applied as a primer in one layer diluted with water up to 50% by weight. Once dry, at least two more layers of ISOPAST must be applied diluted with water up to 25% by weight. Subsequent layers must be applied at right angles to the previous, allowing each layer to dry completely before applying the next one.

For use as primer prior to bonding bituminous waterproofing membranes:

ISOPAST-RUBBER is applied in one layer diluted with water up to 25% by weight. Bonding of the bituminous waterproofing membranes follows after the primer has dried.

Temperature during application should be between +5°C and +35°C. If rainfall or conditions of high relative humidity are expected, application should be postponed.

When ISOPAST is used on surfaces exposed to UV radiation, it must be protected with solar reflective aluminum coating ISOLAC-BT ALU.

Consumption

- Waterproofing roofs: ~2.5 kg/m².
- Waterproofing supporting walls: ~1.5 kg/m².
- Primer for bituminous waterproofing membranes: 0.40-0.60 kg/m².

Consumption depends on substrate type and absorbency.

Packaging

ISOPAST is available in plastic containers of 5 kg & 19 kg.

ISOPAST

Shelf-life - Storage

12 months from production date, in unopened containers, in cool, dry and frost-free conditions, at temperatures higher than +5°C.

Remarks

- ISOPAST is not resistant to organic solvents, oils and strong chemical detergents.
- Avoid contact with eyes and skin. Use protective equipment during application (gloves, protective clothing, eye and face protection). For more information, please consult the relevant Material Safety Data Sheet (MSDS).

Volatile Organic Compounds (VOCs)

According to the Directive 2004/42/CE (Annex II, table A), the maximum allowed VOC content for the product subcategory i, type WB is 140 g/l (2010) for the ready-to-use product.

The ready-to-use product ISOPAST contains a maximum of 140 g/l VOC

ISOMAT S.A.
BUILDING CHEMICALS, MORTARS & PAINTS
HEADQUARTERS – THESSALONIKI, GREECE
17th km Thessaloniki – Ag. Athanasios Road
P.O. BOX 1043, 570 03 Ag. Athanasios, Greece
T +30 2310 576000
www.isomat.eu e-mail: support@isomat.eu